HP 3D High Reusability PA 12

Engineering-grade thermoplastics, optimized for 3D printing efficiency





Picture taken after graphite post-processing

Fine detail and high dimensional accuracy

Get precise small features and detail such as small fine holes, walls and shafts with dimensional accuracy thanks to HP's unique Multi-Agent printing process



Picture taken after dye post-processing

Produce strong quality parts

Robust thermoplastic that optimizes part quality with cost, producing strong structures



Picture taken after dye post-processing

Produce complex parts and lattice structures

Ideal for complex assemblies, housings, enclosures and connectors

Reduce Total Cost of Ownership and produce quality parts with HP 3D High Reusability PA 12, a strong, multi-purpose thermoplastic that enables industry-leading surplus powder reusability.¹

Lowest Cost-Per-Part²

- Optimize cost and part quality,² with a cost-efficient material that offers industry-leading reusability.¹
- No need to throw away reused powder anymore.³
- Produce quality parts batch-after-batch reusing surplus powder time after time.1
- Achieve minimal powder wastage between production cycles.
- No need to track powder history. Stable performance with only 20% refresh rate.1

Optimized for HP Multi Jet Fusion: the best balance between strength and reusability

- A strong thermoplastic for functional prototyping and final parts.
- Optimized for HP's Multi Jet Fusion platform to increase printer safety and deliver truly functional parts.
- Produce high-density parts, with balanced property profiles.
- Excellent chemical resistance to oils, greases, aliphatic hydrocarbons and alkalies.
- Optimal for post finishing processes.

Technical specifications

Measurement	Value	Method
Powder melting point (DSC)	187 °C/369 °F	ASTM D3418
Particle size	60 µm	ASTM 03451
Bulk density of powder	0.425 g/cm ³	ASTM D1895
Density of parts	1.01 g/cm ³	ASTM D792
Tensile Strength, Max Load ⁴ - XY	48 MPa/6960 psi	ASTM D638
Tensile Strength, Max Load ⁴ - Z	48 MPa/6960 psi	ASTM D638
Tensile Modulus ⁴ - XY	1700 MPa/245 ksi	ASTM D638
Tensile Modulus ⁴ - Z	1800 MPa/260 ksi	ASTM D638
Elongation at Break ⁴ - XY	20%	ASTM D638
Elongation at Break ⁴ - Z	15%	ASTM D638
Heat Deflection Temperature (@ 0.45 MPa) - Z	175 ºC/350 ºF	ASTM D648
Heat Deflection Temperature (@ 1.82 MPa) - Z	95 ºC/205 ºF	ASTM D648
	Powder melting point (DSC) Particle size Bulk density of powder Density of parts Tensile Strength, Max Load ⁴ - XY Tensile Strength, Max Load ⁴ - Z Tensile Modulus ⁴ - XY Tensile Modulus ⁴ - Z Elongation at Break ⁴ - XY Elongation at Break ⁴ - Z Heat Deflection Temperature (@ 0.45 MPa) - Z	Powder melting point (DSC)187 °C/369 °FParticle size60 μmBulk density of powder0.425 g/cm³Density of parts1.01 g/cm³Tensile Strength, Max Load ⁴ - XY48 MPa/6960 psiTensile Strength, Max Load ⁴ - Z48 MPa/6960 psiTensile Modulus ⁴ - XY1700 MPa/245 ksiTensile Modulus ⁴ - Z1800 MPa/260 ksiElongation at Break ⁴ - XY20%Elongation at Break ⁴ - Z15%Heat Deflection Temperature (@ 0.45 MPa) - Z175 °C/350 °F

Ordering Information

Product name	HP 3D High Reusability PA 12
Product Number	V1R10A
Weight	13 kg
Compatibility	HP Jet Fusion 3D 4200/3200 Printing Solution
Dimensions	Box: 600 x 333 x 301.8 mm

Eco Highlights

- Powders and agents are not classified as hazardous⁵
- Enclosed printing system and automated powder management, including
- post-processing, for a cleaner and more comfortable environment⁶
- Minimum waste thanks to high reusability of powder¹

Find out more about HP sustainable solutions at hp.com/ecosolutions

1. HP MJF Solution with HP High Reusability PA 12 has the highest post-production surplus powder reusability with 80% reusability vs any other powder based 3DP technology using PA 12 material. Stable performance with only 20% powder refresh rate.

- Based on internal testing and public data, HP Jet Fusion 3D printing solution average printing cost-per-part is half the cost of comparable FDM & SLS printer solutions from \$100,000 USD to \$300,000 USD, when averaged together and not taken individually, on market as of April 2016. Cost analysis based on: standard solution configuration price, supplies price, and maintenance costs recommended by manufacturer. Cost criteria: printing 1 build chamber per day/ 5 days per week over 1 year of 30-gram parts at 10% packing density using the powder reusability ratio recommended by manufacturer.
- 3. Per packing densities >20%.
- 4. Test results realized under the ASTM D638, speciments type V.
- 5. The HP powder and agents do not meet the criteria for classification as hazardous according to Regulation (EC) 1272/2008 as amended.
- 6. The term "cleaner" does not refer to any indoor air quality requirements and/or consider related air quality regulations or testing that may be applicable.

Learn more at hp.com/go/3DMaterials

© Copyright 2016 HP Development Company, L.P. The information contained herein is subject to change without notice. The only warranties for HP products and services are set forth in the express warranty statements accompanying such products and services. Nothing herein should be construed as constituting an additional warranty. HP shall not be liable for technical or editorial errors or omissions contained herein.

